

PRODUCT NAME

29BESB025 – Brushable Black Satin Enamel

PRODUCT DESCRIPTION

A Black Satin Enamel paint that is a very hard and durable, with excellent resistance to petrol, paraffin and mineral oils. Used regularly on products that are subjected to heavy wear, such as machinery.

AVAILABILITY

This product is available in 2.5ltr packs.

FURTHER INFORMATION

This product is specifically designed to be brushed or rolled. Can be thinned by up to 10% maximum. If overcoating is required, 24 hours minimum before application.

VISCOSITY	SPECIFIC GRAVITY	GLOSS
6-8 Poise @ Roto 20c	1.12-1.16 SPL	35-45%

SURFACE PREPERATION AND APPLICATION

Ensure surface has already been primed prior to application of product. Make sure primed surface is free from dust, grease or any other contamination.

APPLICATION AIRLESS SPRAY

Brush or Foam Roller.

HEALTH & SAFETY

Refer to M.S.D.S. 29BESB025 prior to use.

See: <https://www.fhbrundle.co.uk/files/file/sds/29BESB025.pdf>

Provide adequate ventilation.

Prolonged skin contact and inhalation of vapour must be avoided.

Eye contamination - Flush with eyewash or warm water for 10 mins.

Clean hands after use.

Any person or company using this product without first making enquiries as to the suitability for the intended purpose does so at their own risk, and F.H. Brundle can accept no liability for the performance of the product or for any loss or damage arising out of such use.

RECOMMENDED W.F.T.

125-150 microns

RECOMMENDED D.F.T.

40-60 microns

THEORETICAL SPREADING RATE

10-12 Sq. Metres/Litre

DRYING TIME @ 20°C

Surface Dry: 6-8 hours

FLASH POINT 32-55°C

VOC: 530 g/litre

VOLUME SOLIDS

37% (-/+ 2%)

THINNERS

29WS05 White Spirit

SHELF LIFE

12 Months

Issued: 19/01/2022

Whilst every effort has been made to ensure the accuracy of the information supplied, F.H. Brundle cannot be held responsible for any errors or omissions. This product must only be employed for its original intended use. Any other use is wrong and potentially dangerous. Installation must be carried out in full compliance with current regulations. F.H. Brundle cannot be held liable for any damages resulting from wrongful, erroneous or negligent use.

Southampton
Tel: 023 8070 3333
Fax: 023 8070 5555

Rainham
Tel: 01708 25 35 45
Fax: 01708 25 35 50

Ilkeston
Tel: 0115 930 2070
Fax: 0115 951 2455

Birmingham
Tel: 0121 565 8282
Fax: 0121 565 8292

Haydock
Tel: 01942 86 88 88
Fax: 01942 86 88 99

Glasgow
Tel: 0141 773 6699
Fax: 0141 773 6633



F.H.BRUNDLE
SERVING THE TRADE SINCE 1889

www.fhbrundle.co.uk
sales@brundle.com