

**PRODUCT NAME:** Brundle Galvalast

**PRODUCT CODE:** 2903

## PRODUCT DESCRIPTION

A Grey zinc rich brushing primer that is a very hard and durable, with excellent protective properties, for initial surface preparation underneath FH Brundle brushing primers and enamels. Used regularly on products that are subjected to heavy wear, such as machinery.

## AVAILABILITY

This product is available in 400ml packs.

## FURTHER INFORMATION

This product is specifically designed to be brushed or rolled. Can be thinned by up to 10% maximum. If overcoating is required, 24 hours minimum before application.

VISCOSITY	SPECIFIC GRAVITY	GLOSS
6-8 Poise @ Roto 20c	1.26-1.34 SPL	<5%

## SURFACE PREPERATION AND APPLICATION

Make sure primed surface is free from dust, grease or any other contamination.

## APPLICATION AIRLESS SPRAY

Brush or Foam Roller.

## HEALTH & SAFETY

Refer to M.S.D.S. 29PC2903 prior to use. See: <https://www.fhbrundle.co.uk/search?query=2903>

Provide adequate ventilation. Prolonged skin contact inhalation of vapour must be avoided.

Eye contamination - Flush with eyewash or warm water for 10 mins. Clean hands after use.

Any person or company using this product without first making enquiries as to the suitability for the intended purpose does so at their own risk, and F.H. Brundle can accept no liability for the performance of the product or for any loss or damage arising out of such use.

## RECOMMENDED W.F.T.

125-150 microns

## RECOMMENDED D.F.T.

60-80 microns

## THEORETICAL SPREADING RATE

10-12 Sq. Metres/Litre

## DRYING TIME @ 20°C

Surface Dry: 4-6 hours

**FLASH POINT** 32-55°C

**VOC:** 530 g/litre

**VOLUME SOLIDS**

50% ( -/+ 2%)

**THINNERS**

29WS05

**SHELF LIFE**

12 Months

November 2022

Whilst every effort has been made to ensure the accuracy of the information supplied. F.H. Brundle cannot be held responsible for any errors or omissions. This product must only be employed for its original intended use. Any other use is wrong and potentially dangerous. Installation must be carried out in full compliance with current regulations. F.H. Brundle cannot be held liable for any damages resulting from wrongful, erroneous or negligent use.

**Southampton**

**Tel:** 023 8070 3333

**Fax:** 023 8070 5555

**Rainham**

**Tel:** 01708 25 35 45

**Fax:** 01708 25 35 50

**Ilkeston**

**Tel:** 0115 930 2070

**Fax:** 0115 951 2455

**Birmingham**

**Tel:** 0121 565 8282

**Fax:** 0121 565 8292

**Newton-Le-Willows**

**Tel:** 01942 86 88 88

**Fax:** 01942 86 88 99

**Glasgow**

**Tel:** 0141 773 6699

**Fax:** 0141 773 6633



**F.H.BRUNDLÉ**  
SERVING THE TRADE SINCE 1889

**www.fhbrundle.co.uk**  
**sales@brundle.com**