

PRODUCT NAME

29EGW05 – Enamelrite White Gloss

PRODUCT DESCRIPTION

A high gloss topcoat based on SOA resin system. A hard wearing film that gives a smooth finish.

AVAILABILITY

This product is stocked in 5ltr cans.

FURTHER INFORMATION

This product is specifically designed to be sprayed with a maximum thinning ratio of 20%. This product can be over coated after initial surface dry, to achieve desired film thickness.

*Due to the protective nature of the coating, some chalking may occur on exposure/weathering. This is aesthetic and will not deter from the performance of the product.

VISCOSITY	SPECIFIC GRAVITY	GLOSS
6-8 Poise @ Roto 20c	1.04 – 1.08 SPL	Gloss 90%+

SURFACE PREPERATION AND APPLICATION

Ensure surface is free from rust, moisture, oil or other surface contamination. Product should ideally be applied over the top of a suitable primer such as 29BRO or 29ZQDP.

APPLICATION

Product should ideally be applied by spray equipment. Can be brushed or rolled if required.

HEALTH & SAFETY

Refer to M.S.D.S. 29EGW prior to use. See:

Provide adequate ventilation. Prolonged skin contact and inhalation of vapour must be avoided.

Eye contamination - Flush with eyewash or warm water for 10 mins.

Clean hands after use.

Any person or company using this product without first making enquiries as to the suitability for the intended purpose does so at their own risk, and F.H. Brundle can accept no liability for the performance of the product or for any loss or damage arising out of such use.

RECOMMENDED W.F.T.

230-270 microns

RECOMMENDED D.F.T.

70-120 microns

THEORETICAL SPREADING RATE

5-7 Sq. Metres/Litre

DRYING TIME @ 20°C

Surface Dry: 1-2 hours

FLASH POINT 22-32°C

VOC: 530 g/litre

VOLUME SOLIDS

40% (-/+ 2%)

THINNERS

29002 No. 1 Industrial
Thinners

SHELF LIFE

12 Months

Issued: 20/01/2022

Whilst every effort has been made to ensure the accuracy of the information supplied, F.H. Brundle cannot be held responsible for any errors or omissions. This product must only be employed for its original intended use. Any other use is wrong and potentially dangerous. Installation must be carried out in full compliance with current regulations. F.H. Brundle cannot be held liable for any damages resulting from wrongful, erroneous or negligent use.

Southampton
Tel: 023 8070 3333
Fax: 023 8070 5555

Rainham
Tel: 01708 25 35 45
Fax: 01708 25 35 50

Ilkeston
Tel: 0115 930 2070
Fax: 0115 951 2455

Birmingham
Tel: 0121 565 8282
Fax: 0121 565 8292

Haydock
Tel: 01942 86 88 88
Fax: 01942 86 88 99

Glasgow
Tel: 0141 773 6699
Fax: 0141 773 6633



F.H. BRUNDLE
SERVING THE TRADE SINCE 1889

www.fhbrundle.co.uk
sales@brundle.com